

SECTION 101100

SERIES 200

FR701 TEXTILE FABRIC COLORS

A-1
VISUAL
SYSTEMS




F-50 GREEN NEUTRAL




F-51 WHEAT




F-52 SILVER NEUTRAL



F-53 BLUE NEUTRAL




F-54 ROSE QUARTZ



F-55 CRYSTAL BLUE



F-56 QUARTZ



F-57 OPAL



F-58 CHERRY NEUTRAL

SPECIFICATION

Style	2100
Contents	100% Post consumer recycled polyester
Weight	16.5 oz/lineal yard
Width	66" minimum useable
repeat	None

Performance

Breaking strength (ASTM D5034)	150 lbs. min. warp and fill
Tear (ASTM D2261)	30lbs. min. warp and fill
Colorfastness to light (AATCC 16 Option 3)	40 hrs. min.
Colorfastness to crocking (AATCC 8)	class 4 min. dry class 3 min. wet

Cleaning

W-S

Fabric may be cleaned with mild, water-free solvents or water-based cleaning agents or foam.

Acoustical Performance

The net change in Noise Reduction Coefficient (NRC) when an acoustical panel core is covered with FR701 ranges from NRC 0.00 to 0.05

Flammability

ASTM E-84 Class I or A

Colors may vary slightly between dye lots.

Other fabric colors and patterns are available.